



BUREAU  
VERITAS

# TEST REPORT

LAB NO.: (6621)105-0677  
(REVISED)  
FORM NO.: /  
DATE IN: Apr 15, 2021  
DATE OUT: Apr 21, 2021  
NO. OF WORKING DAYS: 5  
REVISED DATE: Apr 27, 2021  
PAGE 1 OF 3

This report is amendment of and supersedes the previous (6621)105-0677 dated Apr 21, 2021.

## OVERALL RATING

PASS X  
FAIL         
DATA       

Vendor:	WUHAN YOUFU INTERNATIONAL TRADE CO.,LTD	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	AAMI PP+PE ISOLATION GOWN LEVEL 2	Style Description:	/
Color:	BLUE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
SKU:	/		

Product Category	/
Test Requested	PARTIAL TEST
Previous Report No.	/

Submitted Fiber Content	70% PP + 30% PE
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

C/N SM/CS-SHUANG/DANA DU

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER RESISTANCE: IMPACT PENETRATION TEST	X			
WATER RESISTANCE: HYDROSTATIC PRESSURE TEST	X			

Revised Reason: As per vendor's request, delete some test in the report.

**Remark:** [BVCPS \(Shanghai\) contact information for this report](#)

**Address:** [No.168, Guanghai Road, Zhuanqiao Town, Minhang, Shanghai, China.](#)

**General Information:**

Jojo Li	086-021-24081666*9309, email: <a href="mailto:jojo-wj.li@cn.bureauveritas.com">jojo-wj.li@cn.bureauveritas.com</a>
Noah Zhang	086-021-24081666*1720, email: <a href="mailto:Xiaoliang.zhang@cn.bureauveritas.com">Xiaoliang.zhang@cn.bureauveritas.com</a>
Seven Sun	086-021-24081666*9327, email: <a href="mailto:Seven.sun@cn.bureauveritas.com">Seven.sun@cn.bureauveritas.com</a>
Du Shuang	086-021-24081666*1709, email: <a href="mailto:shuang.du@cn.bureauveritas.com">shuang.du@cn.bureauveritas.com</a>
Challenge Qiao	086-021-24081666*9331, email: <a href="mailto:challenge.qiao@cn.bureauveritas.com">challenge.qiao@cn.bureauveritas.com</a>
Lizzy Liao	086-021-24081666*9303, email: <a href="mailto:lizzy.liao@bureauveritas.com">lizzy.liao@bureauveritas.com</a>
Sherry Shen	086-021-24081666*9310, email: <a href="mailto:shirley-ll.shen@cn.bureauveritas.com">shirley-ll.shen@cn.bureauveritas.com</a>

**Technical Questions:**

Pat Liu	086-021-24081745, email: <a href="mailto:Pat.liu@cn.bureauveritas.com">Pat.liu@cn.bureauveritas.com</a>
Rio Zhang	86-21-24081666*9305, email: <a href="mailto:Rio.Zhang@cn.bureauveritas.com">Rio.Zhang@cn.bureauveritas.com</a>

BUREAU VERITAS

CONSUMER PRODUCTS SERVICES (SHANGHAI)



JULIA YAN

PROGRAM MANAGER

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>				<u>REQUIREMENTS</u>
<u>WATER RESISTANCE: IMPACT PENETRATION TEST</u> (AATCC 42-17)					
	1	2	3	AVERAGE	
FABRIC (GRAM)	0.0	0.0	0.0	0.0	MAX. 1.0 GRAM
SHOULDER (GRAM)		0.1			MAX. 1.0 GRAM
ARM OPENING (GRAM)		0.2			MAX. 1.0 GRAM
SLEEVE (GRAM)		0.0			MAX. 1.0 GRAM
<u>WATER RESISTANCE: HYDROSTATIC PRESSURE TEST</u> (AATCC 127)					
	1	2	3	AVERAGE	
FABRIC (CMH <sub>2</sub> O)	170	178	171	173	MIN. 20 CMH <sub>2</sub> O
SHOULDER (CMH <sub>2</sub> O)		42.8			MIN. 20 CMH <sub>2</sub> O
ARM OPENING (CMH <sub>2</sub> O)		39.6			MIN. 20 CMH <sub>2</sub> O
SLEEVE (CMH <sub>2</sub> O)		45.2			MIN. 20 CMH <sub>2</sub> O



---

END OF REPORT